

ABSTRACT OF THE DISCLOSURE

A rubber-reinforced styrene transparent resin composition contains a styrene copolymer reinforced with a rubber polymer, wherein the monomer composition of an acetone soluble resin component contained in the resin composition contains 5 to 70% by weight of aromatic vinyl monomer (a1), 30 to 95% by weight of unsaturated carboxylic acid alkyl ester monomer (a2), 0 to 50% by weight of vinyl cyanide monomer (a3), and 0 to 50% by weight of another monomer copolymerizable with these monomers, and the acid value of the acetone soluble resin component is 0.01 to 1 mgKOH/g.